

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	- ≤ 32	≤ 150 ≤ 301	70 55	0.0015 0.0012	0.0040 0.0030	0.0065 0.0050	0.0080 0.0065	0.0100 0.0080					
Free-cutting steels	≤ 25 ≤ 32	≤ 255 ≤ 301	70 55	0.0015 0.0012	0.0040 0.0030	0.0065 0.0050	0.0080 0.0065	0.0100 0.0080					
Unalloyed heat-treatable steels	≤ 20 ≤ 25 ≤ 32	≤ 220 ≤ 255 ≤ 301	70 55	0.0012 0.0012	0.0030 0.0030	0.0050 0.0050	0.0065 0.0065	0.0080 0.0080					
Alloyed heat-treatable steels	≤ 32 ≤ 43	≤ 301 ≤ 402	35	0.0010	0.0025	0.0040	0.0050	0.0065					
Unalloyed case hardened steels	≤ 25	≤ 255	70	0.0015	0.0040	0.0065	0.0080	0.0100					
Alloyed case hardened steels	≤ 32 ≤ 43	≤ 301 ≤ 402	30	0.0010	0.0025	0.0040	0.0050	0.0065					
Nitriding steels	≤ 32 ≤ 43	≤ 301 ≤ 402	25	0.0010	0.0025	0.0040	0.0050	0.0065					
Tool steels	≤ 25 ≤ 43	≤ 255 ≤ 402	35 15	0.0010 0.0007	0.0025 0.0020	0.0040 0.0030	0.0050 0.0040	0.0065 0.0050					
High speed steels	≤ 43	≤ 402	15	0.0007	0.0020	0.0030	0.0040	0.0050					
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48 ≤ 66	≤ 460 -											
Stainless steels, sulphured austenitic martensitic	≤ 28 ≤ 36 ≤ 46	≤ 273 ≤ 337 ≤ 435	25	0.001	0.0025	0.0040	0.0050	0.0065					
Cast iron	≤ 23 ≤ 38	≤ 242 ≤ 354	70 55	0.0015 0.0015	0.0040 0.0040	0.0065 0.0065	0.0080 0.0080	0.0100 0.0100					
Spheroidal graphite iron and malleable cast iron	≤ 23 ≤ 38	≤ 242 ≤ 354	65 45	0.0015 0.0015	0.0040 0.0040	0.0065 0.0065	0.0080 0.0080	0.0100 0.0100					
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20 ≤ 32	≤ 220 ≤ 301											
New cast materials ADI	≤ 32 ≤ 43	≤ 301 ≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25 ≤ 43	≤ 255 ≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	- -	≤ 180 ≤ 180	145 115	0.0017 0.0015	0.0050 0.0040	0.0080 0.0065	0.0100 0.0080	0.0125 0.0100					
Magnesium alloys	-	≤ 120	180	0.0015	0.0040	0.0065	0.0080	0.0100					
Copper, low-alloyed	-	≤ 150	70	0.0012	0.0030	0.0050	0.0065	0.0080					
Brass, short-chipping	-	≤ 180	145	0.0012	0.0030	0.0050	0.0065	0.0080					
Brass, long-chipping	-	≤ 180	90	0.0012	0.0030	0.0050	0.0065	0.0080					
Bronze, short-chipping	-	≤ 180	70	0.0010	0.0025	0.0040	0.0050	0.0065					
Bronze, long-chipping	≤ 25 ≤ 32	≤ 255 ≤ 301	65 45	0.0010 0.0010	0.0025 0.0025	0.0040 0.0040	0.0050 0.0050	0.0065 0.0065					
Duroplastics			35	0.0010	0.0025	0.0040	0.0050	0.0065					
Thermoplastics			55	0.0012	0.0030	0.0050	0.0065	0.0080					
Reinforced plastics - Kevlar													
Reinforced plastics - GFK / CFK													

Material group	Hardness		SFM	Feed Rate - IPR									
	HRC	BHN		1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	- ≤ 32	≤ 150 ≤ 301	100 80		0.0050 0.0040	0.0080 0.0065	0.0100 0.0080	0.0125 0.0100	0.0125 0.0100	0.0140 0.0110	0.0160 0.0125	0.0200 0.0160	0.0245 0.0200
Free-cutting steels	≤ 25 ≤ 32	≤ 255 ≤ 301	100 80		0.0050 0.0040	0.0080 0.0065	0.0100 0.0080	0.0125 0.0100	0.0125 0.0100	0.0140 0.0110	0.0160 0.0125	0.0200 0.0160	0.0245 0.0200
Unalloyed heat-treatable steels	≤ 20 ≤ 25 ≤ 32	≤ 220 ≤ 255 ≤ 301	100 80		0.0040 0.0040	0.0065 0.0065	0.0080 0.0080	0.0100 0.0100	0.0100 0.0100	0.0110 0.0110	0.0125 0.0125	0.0160 0.0160	0.0200 0.0200
Alloyed heat-treatable steels	≤ 32 ≤ 43	≤ 301 ≤ 402											
Unalloyed case hardened steels	≤ 25	≤ 255	100		0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	0.0245
Alloyed case hardened steels	≤ 32 ≤ 43	≤ 301 ≤ 402											
Nitriding steels	≤ 32 ≤ 43	≤ 301 ≤ 402											
Tool steels	≤ 25 ≤ 43	≤ 255 ≤ 402	50		0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	0.0160
High speed steels	≤ 43	≤ 402											
Spring steels	≤ 38	≤ 354											
Hardened steels	≤ 48 ≤ 66	≤ 460 -											
Stainless steels, sulphured austenitic martensitic	≤ 28 ≤ 36 ≤ 46	≤ 273 ≤ 337 ≤ 435											
Cast iron	≤ 23 ≤ 38	≤ 242 ≤ 354	100 80		0.0050 0.0050	0.0080 0.0080	0.0100 0.0100	0.0125 0.0125	0.0125 0.0125	0.0140 0.0140	0.0160 0.0160	0.0200 0.0200	0.0245 0.0245
Spheroidal graphite iron and malleable cast iron	≤ 23 ≤ 38	≤ 242 ≤ 354	90 65		0.0050 0.0050	0.0080 0.0080	0.0100 0.0100	0.0125 0.0125	0.0125 0.0125	0.0140 0.0140	0.0160 0.0160	0.0200 0.0200	0.0245 0.0245
Chilled cast iron	≤ 38	≤ 354											
New cast materials GGV	≤ 20 ≤ 32	≤ 220 ≤ 301											
New cast materials ADI	≤ 32 ≤ 43	≤ 301 ≤ 402											
Special alloys	≤ 54	≤ 549											
Ti and Ti-alloys	≤ 25 ≤ 43	≤ 255 ≤ 402											
Aluminium and Al-alloys	-	≤ 120											
Al wrought alloys	-	≤ 200											
Al cast alloys ≤ 10 % Si ≤ 24 % Si	- -	≤ 180 ≤ 180	205 160		0.0065 0.0050	0.0100 0.0080	0.0125 0.0100	0.0160 0.0125	0.0160 0.0125	0.0180 0.0140	0.0200 0.0160	0.0245 0.0200	0.0290 0.0245
Magnesium alloys	-	≤ 120	260		0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	0.0245
Copper, low-alloyed	-	≤ 150	100		0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	0.0200
Brass, short-chipping	-	≤ 180											
Brass, long-chipping	-	≤ 180	130		0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	0.0200
Bronze, short-chipping	-	≤ 180	100		0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	0.0160
Bronze, long-chipping	≤ 25 ≤ 32	≤ 255 ≤ 301	90 80		0.0030 0.0030	0.0050 0.0050	0.0065 0.0065	0.0080 0.0080	0.0080 0.0080	0.0090 0.0090	0.0100 0.0100	0.0125 0.0125	0.0160 0.0160
Duroplastics			50		0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	0.0160
Thermoplastics			80		0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	0.0200
Reinforced plastics - Kevlar													
Reinforced plastics - GFK / CFK													